

AGUAPLACK QUICK JOINT 30 MIN

Quick setting and drying gypsum-based compound for joint filling and finishing.



GENERAL CHARACTERISTICS

USAGES

- For use on gypsum boards and plasterboards.
- Joint filling and Finishing.
- Fixing cornerbeads and patching screw heads.
- Suitable for achieving all Quality Levels Q1 to Q4, from joint filling to skim coating to the highest quality standard.
- Can be used for repairing small holes and cracks on plaster or plasterboard.

CHARACTERISTICS

- Special additives allow a fast, lump-free, adequate consistency mix.
- Good filling capacity, low shrinkage.
- Excellent sanding characteristics
- Extra fine particle size performs to a smooth and quality finish.
- Suitable for difficult installation conditions, such as colder temperatures and air humidity.
- Ideal for quick renovation work.

TECHNICAL DATA

| Product | |
|-------------------|---|
| Form | Powder |
| Composition | Gypsum, inorganic fillers, binders, additives |
| Color | White |
| Particle size | Fine < 200µ |
| Density | 0,75 g/cm3 |
| Reaction to fire | A2-s1, d0. Not flammable |
| Application | |
| Temperature | 5-35 °C |
| Tools | Jointing knife, blade, spatula |
| Mixing rate | 0,50 L / 1kg |
| Working time | Approx. 30' at 20°C |
| Setting time | Approx. 30' at 20°C |
| Consumption | Jointing: Aprox. 0,3 kg/m Skimming: 1,0 kg/m2/mm |
| Interior/Exterior | Interior |

PACKING

| Product Code | Packaging | Units/Carton | Palletization |
|--------------|------------|--------------|---------------|
| 70015-001 | Sack 5 kg | - | 140 sack |
| 70015-002 | Sack 20 kg | - | 50 sack |

PREPARATION AND APPLICATION

SUBSTRATE PREPARATION

Support must be clean, dry and dust-free. Remove dust from joints. Use clean water, container and tools to mix the product. Add 2 parts powder to 1 part water (20 Kg powder – approximately 10 L water). Stir vigorously, preferably with electric stirrer, to produce a uniform and even paste. Wait for 1 minute before use. Powder-water proportion can be adjusted depending on the consistency required. The paste remains workable for approx. 30 minutes at 20°C. High temperatures may shorten and cold temperatures may extend working time.

Do not stir once the setting process has begun. Do not add water nor powder once the setting process has begun. Do not add water in excess to avoid shrinkage.

APPLICATION

Fill the joint and centre the tape over the joint, then embed by pressing down with a spatula and overcoat immediately. Apply the 2nd coat by exceeding 3 to 5 cm from each side of the joint. Allow air ventilation to ensure a correct drying process. Sand only when the compound is thoroughly dry. Once the surface is dry, apply Beissier Drywall Primer in preparation for painting or Beissier Fixacryl in preparation for wallcoverings. Tools: Jointing knife, blade, spatula. Clean tools with water immediately after use. In general, substrates must be treated and prepared according to local standards. If in doubt, it is highly recommended to perform a test application on a small area to determine suitability, compatibility and application conditions.

CAUTIONS, STORAGE, HEALTH AND SAFETY

CAUTIONS

Do not apply at temperatures below 5°C or above 35°C. Do not apply on substrates subjected to constant humidity. For joint filling, always use a paper or fibreglass mesh tape. Do not mix with adhesive plaster or other materials.

STORAGE AND SHELF LIFE.

Store away from extreme temperatures, frost, direct sunlight and humidity. Guaranteed preservation period: 12 months. The best quality is guaranteed within original unopened package. Open packages should be consumed within the soonest possible time. Date of manufacture can be read as printed on package and/or concluded out of batch number YDDD##. Example: Batch Nr. 114401 = 2021 May 24 (144/365) Close properly after use.

HEALTH AND SAFETY

Consult the latest Safety Data Sheet available at www.beissier.com. Avoid direct contact with skin and eyes. In case of prolonged contact, it is recommended to wear gloves and glasses. Avoid inhalation of particles when sanding. Keep out of reach of children.

DISPOSAL PROCEDURES

Dispose of waste and residues in accordance with local authority requirements. Powder to be collected, sealed tightly in bags and disposed on approved landfills. Paste must not be thrown away into drains. If recycling is not practicable, dispose of in compliance with local regulations.

REGULATIONS AND CERTIFICATIONS

Applicable Norms and Certificates:

Classification EN-13963:2005



BEISSIER S.A.U. 06
 Pol. Txirrita Maleo. 14 B.0025
 E-20100 Errenteria. España

AGUAPLACK QUICK JOINT 30 min
 EN 13963:2005
 Joint compound for laminated gypsum board joints. Type 3B.
 Reaction to fire A2 s1, d0

Environmental Certifications:



Note: The purpose of this data sheet is to inform our customers about our product's properties. The information presented in the sheet is based on the current state of our knowledge. However, this information is no substitute for a description pertaining specifically to the type and condition of the substrate concerned. Since technical progress is continuously being made, it is our customer's responsibility prior to use, to check with us that updated edition of this sheet has not been issued.